



**DOLPHIN 510 GENERAL PURPOSE NEUTRAL SILICONE SEALANT**

**DOLPHIN 510 GENERAL PURPOSE NEUTRAL SILICONE SEALANT** is a high performance, UV-resistant, one-component, neutral-cure silicone sealant. **DOLPHIN 510 GENERAL PURPOSE NEUTRAL SILICONE SEALANT** is an industrial grade, neutral silicone sealant designed for sealing lap joints in metal guttering, aluminum roofing flashing and down pipes.



**TECHNICAL PROPERTIES**

Properties	Test Method	Unit	Specifications
Chemical Base			1-C Silicone
Cure Mechanism			Moisture
Cure Type			Neutral
<i>As Supplied @ 25°C, 50% RH</i>			
Color			Clear, White, Black
Consistency			Homogeneous paste
Specific Gravity	ASTM D 1475		1.00 ± 0.02
Flow Properties	ASTM C 639	mm	0 (Non-sag)
Skin Over Time	ASTM C 679	minutes	Approx. 7
Tack Free Time	ASTM C 679	minutes	Approx. 12
Depth Cure, 24 hrs	Lab Test	mm	~ 2.5
<i>As Cured – 7 Days @ 25°C, 50% RH</i>			
Hardness (Shore A)	ASTM D 2240	Points	30 – 35
Tensile Strength	ASTM D 412	N/mm <sup>2</sup>	≤ 1.10
Elongation	ASTM D 412	%	≤ 700
Young’s Modulus	ASTM D 412	MPa	≤ 0.30
Service Temp.		°C	-20 to +200

*Note:*

\* Curing time (Skin Over Time & Tack Free Time) may vary depending on climatic condition during application.

\* Information on this data sheet is subject to change without prior notice and should not be used for writing specifications.

**TYPICAL USES**

- Metal roofing system
- Flash down pipes
- Skylights & extraction units
- Pipe or sprinkler system penetrations
- Air conditioning
- Sheet metal
- General purpose adhering & sealing for building materials, steel, aluminum, concrete, brick and masonry block or brick work.

**KEY FEATURES**

- Non-corrosive
- Neutral cure/low odor
- Non-sag
- Extremely durable
- Primerless adhesion to most materials



## DOLPHIN 510 GENERAL PURPOSE NEUTRAL SILICONE SEALANT

<b>COLORS</b>	<b>DOLPHIN 510 GENERAL PURPOSE NEUTRAL SILICONE SEALANT</b> is available in Clear, White and Black colors. RAL* colors are available upon request. *Special color orders may require lead time and minimum order quantities.
<b>PACKAGING</b>	<b>DOLPHIN 510 GENERAL PURPOSE NEUTRAL SILICONE SEALANT</b> is available in standard caulking cartridges (280ml), packed sausages (600ml) and 200 Liter drum.
<b>SURFACE PREPARATION</b>	The substrate areas that will be in contact with sealant must be clean, dry and free of all loose materials, dust, dirt, rust, oil and other contaminants. Non-porous substrates should be cleaned with a solvent and a clean, lint-free, cotton cloth. Wipe dry immediately with another such cloth before the solvent evaporates from the surface.
<b>TOOLING AND FINISHING</b>	Immediately tool sealant after application and before skin formation. Tooling of sealant should be done in one continuous stroke. Remove masking tape immediately after tooling is completed.
<b>CLEANUP AND REMOVAL</b>	Uncured sealant may be removed from tools, equipment and non-porous surfaces with solvents. For porous substrates, allow the sealant to cure before removal by peeling or other mechanical means. Cured sealant can only be removed mechanically.
<b>LIMITATIONS</b>	Not paintable.
<b>STORAGE AND SHELF LIFE</b>	When stored in original unopened container at or below 77°F (25°C) in dry warehouse conditions, <b>DOLPHIN 510 GENERAL PURPOSE NEUTRAL SILICONE SEALANT</b> has a shelf life of 12 months from manufacturing date. Containers should always be kept sealed when not in use.
<b>HANDLING PRECAUTIONS</b>	Use in well-ventilated area. Direct contact of uncured sealant may irritate eyes and skin. Over exposure to vapor may irritate eyes, nose and throat. Do not handle contact lenses with sealant on hands. In case of eye contact, flush eyes with water for 15 minutes. Obtain medical attention. In case of skin contact, remove from skin and flush with water.

**KEEP OUT OF REACH OF CHILDREN • KEEP CONTAINER TIGHTLY CLOSED • FOR INDUSTRIAL & PROFESSIONAL USE**

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made. AMI reserves the right to change the properties of its products without notice.

**AL MUQARRAM INSULATION MATERIALS INDUSTRY, LLC**

P.O. Box: 24753, Sharjah, UAE

Phone: + 971 6 5353796

Fax: +971 6 5353964

E-mail: [info@muqarram.com](mailto:info@muqarram.com), [sales@muqarram.com](mailto:sales@muqarram.com)