

HI-STICK AEROSOL SPRAY PAINT

Product Description:

AMAF acrylic spray paint is made from 100 % Acrylic resin and CFC free advanced technology. Its film finish has excellent hardness with excellent weather resistance.

Product Features:

HISTICK SPRAY PAINT has good leveling, high coverage, high spray rate, fast dry, strong adhesiveness, rich color, high user and high gloss.

Product Description	AEROSOL SPRAY PAINT
Brand Name	HI-STICK
Manufacturer	AL MUQARRAM AIR FRESHENER & PAINTS INDUSTRY L.L.C

Typical Properties:

S. No.	PROPERTIES	DETAILS
1	Composition	Pure Acrylic Polymer + Pigment + Solvents + Standard CFC Free Gas
2	Specific Gravity	0.90±0.05
3	%NVA - ASTM - D1644	18% ± 3.00
4	Viscosity on Zhan Cup	30.00 ± 3 sec
5	Inside Pressure MPa @28C°	0.4-0.5 MPa
6	Flash Point ASTM - D93	7.00 ± 3
7	5-8 minutes	5-8 minutes
8	Hard dry ASTM – D – 1640	Minimum 1 hour
9	Finish	Smooth
10	Film hardness ASTM D - 3363	Flexible, Hard film
11	Res. to washing & abrasion	Satisfactory
12	Res. to heat and humidity	Satisfactory up to 60C° with high humidity
13	Hot water test	Passes and satisfactory
14	Filling ratio	Max 90% of the total volume of can
15	Recommendations	Decorative & Industrial Use (Exterior and Interior)
16	Spray Rate	98% STD – Result 99%
17	Shelf Life	3 Years



Made in U.A.E

AL MUQARRAM AIR FRESHENERS AND SPRAY PAINTS INDUSTRY L.L.C

P.O. BOX # 24756, UMM AL QUWAIN. U.A.E

PHONE: +971 6 5353796, FAX: +971 6 5353964

EMAIL: info@muqarram.com, sales@muqarram.com

WEBSITE: www.muqarram.com

HI-STICK AEROSOL SPRAY PAINT

Application areas:

It can be used widely in interior and exterior surfaces like in finishing and mending of metal, wood, glass, leather, ceramics and plastics.

Surface preparation and application information:

Clean the surface if it is dusty, oily or greasy. If rusted sand those areas prior to spray paint application. Check the actuator and clean it, if necessary. Shake well before using the paint. Spray the paint on rough surface once to judge the internal pressure. Spray exactly parallel from the start till end in to and fro motion. The minimum distance of 8-10" should be kept between the can and the substrate.

Caution:

Do not use near flames, sparks, direct sunlight, heat and etc. Pressurized container and do not expose to heat beyond 50°C. Do not puncture and incinerate the can.

Storage, Shelf life:

When stored the can in a cool and dry place below 25°C the HISTICK SPRAY PAINT has a shelf life of 3 years from the date of manufacture. Storage outside may reduce the shelf life.

Packing/Size:

Each HISTICK SPRAY PAINT can has a volume of 400 ml. 12 cans are packed in a carton.

Shipping/Transport Information:

UN No. Sea/Air	:	1950
Shipping Name	:	Aerosol Spray Paint
Technical/Chemical Name	:	Aerosol Spray Paint
IMDG Class	:	2.1
IMDG Page No.	:	2102
Subsidiary Hazard (S) IMO Class & Division	:	2.1
Emergency Schedule (EMS)	:	F-D, S-U
Marine Pollutant	:	No



Made in U.A.E

AL MUQARRAM AIR FRESHENERS AND SPRAY PAINTS INDUSTRY L.L.C

P.O. BOX # 24756, UMM AL QUWAIN, U.A.E

PHONE: +971 6 5353796, FAX: +971 6 5353964

EMAIL: info@muqarram.com, sales@muqarram.com

WEBSITE: www.muqarram.com