

TECHNICAL DATA SHEET

DOLPHIN 200 GP PRO SILICONE SEALANT

Revision Date: 20th Sept, 2022


Revision No. 1

Number of Pages: 2

PRODUCT DESCRIPTION

Dolphin 200 GP PRO Silicone Sealant is a new addition to the innovative range of acetic sealants specially designated to professional use. It is single component silicone that cures to atmospheric moisture. It exhibits negligible shrinkage to perfection. Dolphin 200 GP PRO is permanently elastic after curing. It has an excellent sealing and bonding capability with potential anti fungicide property to prevent mould/bacteria growth.

TECHNICAL PROPERTIS



Properties	Test Method	Unit	Specification
Chemical Base			1-C Silicone
Cure Mechanism			Moisture
Cure Type			Acetoxy
As Supplied @ 25°C, 50% RH			
Color			Translucent, White, Black
Consistency			Homogeneous
Density	ASTM D1475	g/cm3	0.978 ± 0.02
Flow Properties	ASTM C 639	mm	Non-Sag
Skin Over Time	ASTM C 679	Minutes	Approx.5
Tack Free Time	ASTM C 679	Minutes	Approx.10
Depth Cure, 24 Hrs	Lab Test	Mm	~ 1.65
As Cured – 7 Days @ 25°C, 50% RH			
Hardness, (Shore A)	ASTM D 2240	Points	23.0 – 26.0
Tensile Strength	ASTM D 412	N/mm2	~ 1.17
Elongation	ASTM D 412	%	~ 500
Young's Modulus	ASTM D 412	MPa	~ 0.24
Service Temp.		°C	- 20 to + 220
Application Temp.		°C	5 to 45

Note:

* Curing time (Skin Over Time & Tack Free Time) may vary depending on climatic condition during application.

* Information on this data sheet is subject to change without prior notice and should not be used for writing Specifications.

TYPICAL USES

- Sealing construction joints in concrete structures
- Sealing masonry joints, balcony, window and door perimeter joints
- Galvanized Aluminium cladding joints
- Galvanized Aluminium angle joints
- Pinhole and shower screen repair

KEY FEATURES

- Antifungal & Antibacterial
- Negligible Shrinkage

COLORS	DOLPHIN 200 GP PRO Silicone Sealant is available in Translucent, White, Red, Black and Grey.
PACKAGING	DOLPHIN 200 GP PRO Silicone Sealant is available in collapsible tubes (90ml), standard caulking cartridges (280 ml) and 200 Liter drum.
SURFACE PREPARATION	The substrate areas that will be in contact with sealant must be clean, dry and free of all loose materials, dust, dirt, rust, oil and other contaminants. Non - porous substrates should be cleaned with a solvent and a clean, lint - free, cotton cloth. Wipe dry immediately with another such cloth before the solvent evaporates from the surface.
JOINT DIMENSIONS	Joint dimensions: Min. width for joints: 5 mm, Max. width for joints: 30 mm, Min. depth for joints: 5 mm. Recommendation Sealing jobs: Joint width= 2 X Joint depth
TOOLING AND FINISHING	Immediately tool sealant after application and before skin formation. Tooling of sealant should be done in one continuous stroke. Remove masking tape immediately after tooling is completed.
CLEANUP AND REMOVAL	Uncured sealant may be removed from tools, equipment and non-porous surfaces with solvents. For porous substrates, allow the sealant to cure before removal by peeling or other mechanical means. Cured sealant can only be removed mechanically.
LIMITATIONS	Not paintable. May not be suitable to join sensitive natural stones such as marble, granite or quartz, as this may cause staining. Not to be used in contact with sensitive metals such as lead, copper, brass, zinc, carbon steel, galvanized iron or magnesium as corrosion may occur during acetic acid release/sealant cure. Substrate compatibility test is always recommended.
STORAGE AND SHELF LIFE	When stored in original unopened container at or below 77°F (25°C) in dry warehouse conditions, DOLPHIN 200 GP PRO SILICONE SEALANT has a shelf life of 15 months from manufacturing date. Containers should always be kept sealed when not in use
HANDLING PRECAUTIONS	Use in well-ventilated area. Direct contact of uncured sealant irritates eyes and may irritate skin. Over exposure to vapor may irritate eyes, nose and throat. Do not handle contact lenses with sealant on hands. In case of eye contact, flush eyes with water for 15 minutes. Obtain medical attention. In case of skin contact, remove from skin and flush with water. Keep out of reach of children Keep container tightly closed For Industrial & Professional use

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made. AMI reserves the right to change the properties of its products without notice