

TECHNICAL DATA SHEET

DOLPHIN 500 Neutralseal Sealant

Revision Date : 8th Feb 2023

Revision No. 5

Number of Pages : 2

PRODUCT DESCRIPTION

Dolphin 500 Neutralseal premium silicone sealant is a versatile neutral oxime grade, one component, non – slump, 100% polymer which cures to form a high strength durable and elastic rubber seal with excellent adhesion. It is perfectly formulated for sanitary and general construction applications. It is an anti – fungal silicone which forms permanent bonding after curing. It has non – corrosive property and 50% joint movement capability. This product is odorless, resistant to UV & Water.

TECHNICAL PROPERTIES



Properties	Test Method	Unit	Specifications
Chemical Base			1-C Silicone
Cure Mechanism			Moisture
Cure Type			Neutral
As Supplied @ 25° C, 50% RH			
Color			Clear, White, Black
Consistency			Homogeneous paste
Density	ASTM D 1475		1.01 ± 0.01
Flow Properties	ASTM C 639	mm	0 (Non-sag)
Skin Over Time	ASTM C 679	minutes	Approx. 5
Tack Free Time	ASTM C 679	minutes	Approx. 10
Depth Cure, 24 hrs	Lab Test	mm	~ 2.5
As Cured - 7 Days @ 25° C, 50% RH			
Hardness (Shore A)	ASTM D	Points	24 – 28
Tensile Strength	ASTM D 412	N/mm ²	< 1.10
Elongation	ASTM D 412	%	≤ 750
Young's Modulus	ASTM D 412	MPa	< 0.30
Service Temp.		°C	-40 to +250
Application Temp.		°C	5 – 45

Note:

* Curing time (Skin Over Time & Tack Free Time) may vary depending on climatic condition during application.

* Information on this data sheet is subject to change without prior notice and should not be used for writing specifications

TYPICAL USES

- Sealing of expansion joints in concrete, brickwork, curtain wall construction.
- Kitchen, bathrooms and showers. General sealing and waterproofing.
- General construction ,vinyl, aluminium and metal sliding.
- General Construction
- Suitable for internal application.
- Metal Building and Portable Housing Applications
- Nonstructural Glazing applications.

KEY FEATURES

- 100% Polymer
- Excellent Adhesion
- Negligible Shrinkage
- Non-corrosive & odourless
- Non-stain.

COLOR	DOLPHIN 500 Neutralseal Sealant is available in Clear, White, Black and Grey. RAL* colors are available upon request. *Special color orders may require lead time and minimum order quantities.
PACKAGING	DOLPHIN 500 Neutralseal Sealant is available in standard caulking cartridges (280ml), packed sausages (600ml) and 200 Liter drum.
SURFACE PREPARATION	The substrate areas that will be in contact with sealant must be clean, dry and free of all loose materials, dust, dirt, rust, oil and other contaminants. Non - porous substrates should be cleaned with a solvent and a clean, lint - free, cotton cloth. Wipe dry immediately with another such cloth before the solvent evaporates from the surface.
JOINT DIMENSIONS	Joint dimensions: Min. width for joints: 5 mm, Max. width for joints: 30 mm, Min. depth for joints: 5 mm. Recommendation Sealing jobs: Joint width= 2 X Joint depth
TOOLING AND FINISHING	Immediately tool sealant after application and before skin formation. Tooling of sealant should be done in one continuous stroke. Remove masking tape immediately after tooling is completed.
APPLICATION INSTRUCTION	Cut nozzle in V-shape and at a sharp angle slightly wider than the desired bead. Screw nozzle on the cartridge. Can easily be extruded with a hand- or air pressure gun at temperatures between +5°C and 35°C.
CLEANUP AND REMOVAL	Uncured sealant may be removed from tools, equipment and non-porous surfaces with solvents. For porous substrates, allow the sealant to cure before removal by peeling or other mechanical means. Cured sealant can only be removed mechanically.
LIMITATION	Not paintable.
STORAGE AND SHELF LIFE	When stored in original unopened container at or below 77°F (25°C) in dry warehouse conditions, DOLPHIN 500 Mirror Sealant has a shelf life of 18 months from manufacturing date. Containers should always be kept sealed when not in use
HANDLING PRECAUTIONS	Use in well-ventilated area. Direct contact of uncured sealant may irritate eyes and skin. Over exposure to vapor may irritate eyes, nose and throat. Do not handle contact lenses with sealant on hands. In case of eye contact, flush eyes with water for 15 minutes. Obtain medical attention. In case of skin contact, remove from skin and flush with water.

KEEP OUT OF REACH OF CHILDREN • KEEP CONTAINER TIGHTLY CLOSED • FOR INDUSTRIAL & PROFESSIONAL USE

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made. AMI reserves the right to change the properties of its products without notice