

TECHNICAL DATA SHEET

DOLPHIN PU 45 SEALANT

Revision Date : 24th Jan 2023

Revision No. 1

Number of Pages : 2

PRODUCT DESCRIPTION

DOLPHIN PU 45 SEALANT is a high quality, neutral, elastic, 1-component construction joint and adhesive sealant based on polyurethane.

TECHNICAL PROPERTIS



Properties	Specifications
Basis	Polyurethane
Consistency	Stable paste
Curing system	Moisture curing
Skin formation* (23°C/50% R.H.)	Ca. 35 min
Curing speed * (23°C/50% R.H.)	Ca. 4 mm/24h
Hardness**	40 ± 5 Shore A
Density	Ca. 1.41 g/ml
Maximum allowed distortion	± 20 %
Max. tension (ISO 37)**	Ca. 2.15 N/mm ²
Elasticity modulus 100% (ISO 37)**	Ca. 1.35 N/mm ²
Elongation at break (ISO 37)**	> 700 %
Temperature resistance**	-30 °C → 90 °C
Application temperature	5 °C → 35 °C

Note:

Curing time may vary depending on climatic condition during application.

Information on this data sheet is subject to change without prior notice and should not be used for writing specifications

**These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. ** This information relates to fully cured product.*

PROPERTIES

- Very easy to apply
- Permanently elastic after curing
- Excellent resistance to UV radiation
- Very good adhesion on many materials
- Excellent resistance to many chemicals
- Not suitable for natural stone
- Paintable

APPLICATIONS

- All sealing and bonding applications in the building industry.
- Structural bonding in vibrating constructions.
- Sealing of shrinking joints in concrete floors.
- Bonding of roof tiles.

APPLICATION METHOD	<ul style="list-style-type: none"> • Application method: With a manual, pneumatic or accu caulking gun. • Cleaning: Clean with Surface Cleaner, immediately after use Cured DOLPHIN PU 45 SEALANT can only be removed mechanically. • Finishing: With a soapy solution or Finishing Solution before skinning. • Repair: With the same material.
PACKAGING	Colour: white, black, grey, concrete grey Packaging: 280 ml
STORAGE AND SHELF LIFE	12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.
SUBSTRATES	<p>Substrates: all usual building substrates, metals, polyesters, ... Nature: rigid, clean, dry, free of dust and grease. Surface preparation: DOLPHIN PU 45 SEALANT has a good adhesion to most substrates. However, for optimal adhesion and in critical applications, such as joints exposed to extreme weather conditions, high- or water- loaded joints, we recommend to follow a pre- treatment procedure. Apply Primer 100 on porous substrates. Prepare non-porous surfaces with a activator or cleaner (see Technical Data Sheet).</p> <p>There is no adhesion on PE, PP, PTFE (Teflon®) and bituminous substrates. We recommend a preliminary adhesion and compatibility test on every surface.</p>
JOINT DIMENTIONS	<p>Min. width for bonding: 2 mm Min. width for joints: 5 mm Max. width for bonding: 10 mm</p> <p>Max. width for joints: 30 mm Min. depth for joints: 5 mm Recommendation sealing jobs: joint width = 2 x joint depth.</p>
HEALTH AND SAFETY RECOMMENDATION	Take the usual labor hygiene into account. Consult label and material safety data sheet for more information.
ENVIRONMENTAL CLAUSES	<p>LEED regulation:</p> <p>DOLPHIN PU 45 SEALANT conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED 2009 Credit 4.1: Low- Emitting Materials – Adhesives & Sealants concerning the VOC-content.</p>
LIABILITY	The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.
REMARKS	<p>DOLPHIN PU 45 SEALANT is paintable with most water based paints, however due to the large number of paints and varnishes available we strongly suggest a compatibility test before application.</p> <p>DOLPHIN PU 45 SEALANT cannot be used as a glazing sealant.</p> <p>Do not use in applications where continuous water immersion is possible.</p> <p>It is recommended to do a compatibility test prior to application.</p> <p>DOLPHIN PU 45 SEALANT has a good UV resistance but can discolor under extreme conditions or after very long UV exposure.</p> <p>Contact with bitumen, tar or other plasticizer releasing materials such as EPDM, neoprene, butyl, etc. is to be avoided since it can give rise to discoloration and loss of adhesion.</p> <p>Do not apply or allow to cure in the presence of uncured silicone sealants, alcohol - or other solvent cleaners.</p> <p>When using different reactive joint sealants, the first joint sealant must be completely hardened before the next one is applied.</p>

KEEP OUT OF REACH OF CHILDREN • KEEP CONTAINER TIGHTLY CLOSED • FOR INDUSTRIAL & PROFESSIONAL USE

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made. AMI reserves the right to change the properties of its products without notice