



WORLD-CLASS CHEMICALS


TECHNICAL DATA SHEET

DOLPHIN CPVC ADHESIVE		
Revision Date: 1 st April 2021	Revision No: 02	Number of Pages: 2

PRODUCT DESCRIPTION

Dolphin CPVC Adhesive medium-bodied orange cement for bonding all schedules and classes of CPVC pipes and fittings up to 6" diameter with an interference fit. For Residential and commercial hot and cold-water system, up to 200°F / 93°C. Recommended application temperature 40°F to 110°F / 4°C to 43°C.

TECHNICAL PROPERTIES

	Properties	Specifications
	Appearance	Flowing, medium-viscosity liquid
	Color	Orange
	Odor	Sweet aromatic
	Specific Gravity	0.96 ± 0.02 g/cm ³
	Viscosity @25°C (Sp#4, RPM#50)	900 ± 300 cPs
	Solubility in water (after cure)	Insoluble
	Set Time	5-15 mins depending on temp.
	Full Cure (pressure application)	24 hours at ambient temp.
	Pressure can withstand	16 Bar
	Service Temperature	70°C
	Note: * Curing time (Skin Over Time & Tack Free Time) may vary depending on climatic condition during application.	

(Information on this data sheet is subject to change without prior notice and should not be used for writing specifications)

KEY FEATURES

- One-Part Application
- Comes with Built-in Brush
- Rapid Curing
- Strong and Durable Bonding
- Safe to use for bonding Drinking water flowing pipes
- Meets BS & ASTM standards
- Easy to use

Packaging	Dolphin CPVC Adhesive is available in tin cans of 946 ml, 476 ml, 237 ml, and 118 ml
Precautions	<ul style="list-style-type: none"> • Flammable liquid, avoid excessive heat and avoid areas with ignition sources • Do not smoke while applying • This product is intended for use by skilled individuals at their own risk. It is highly recommended that the installer reviews the instructions supplied by the pipe and fitting manufacturer



WORLD-CLASS
CHEMICALS

Application Instruction	<ul style="list-style-type: none"> • Cut CPVC pipe in right angles chamfer outside at 15° angle and smoothen rough edges • Insert pipe in the fitting and mark depth? Thoroughly clean both surfaces using Acetone solvent and tissue paper • Stir the adhesive well before application • Apply a uniform layer of adhesive in an axial direction using a brush with a thin layer on the fitting and thicker layer on the pipe • Put the parts together within 4 minutes (at 23°C) without turning and hold them firmly for a few seconds • Wipe off excess adhesive immediately • Allow the assembled joint to settle for 5 minutes (15 min. if temp. is below 10°C) • For better results, use assembled pipe after one hour. After full curing, allow free flow of water through the pipe for a few minutes to rinse it before use
Cleaning	Any wet or partially wet adhesive can be removed with scraping and acetone solvent. Dried adhesive is best removed mechanically or with a scraper or by sanding.
Storage and shelf life	When stored in original unopened container below 25°C, in cool, dry condition, away from direct sunlight, away from direct flame and in a well-ventilated area, Dolphin CPVC Adhesive has a shelf life of 12 months from date of manufacturing. Keep containers securely sealed. Storage outside these parameters may dramatically reduce its shelf life.
Health and Safety	<ul style="list-style-type: none"> • Use with adequate ventilation. If working in an area with poor ventilation or in a confined area, recommend a mask be worn • Avoid eye and skin contact and avoid breathing in vapor • Always wash hands before breaks and after finishing work • In case of skin contact, wipe off excess and remove contaminated clothing immediately and flush with soap and water <p>Full details are available on the product Safety Data Sheets. To ensure no harm is caused to persons using AMI products, it is recommended that the appropriate Safety Data Sheets are read by all concerned. Visit www.muqarram.com for copies.</p>

KEEP OUT OF REACH OF CHILDREN • KEEP CONTAINER TIGHTLY CLOSED • FOR INDUSTRIAL & POFESSIONAL USE

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made. AMI reserves the right to change the properties of its products without notice.

