

TECHNICAL DATA SHEET

DOLPHIN FIRE-STOP SILICONE SEALANT

Revision Date: 8th Feb 2023

Revision No: 5

Number of Pages: 3

PRODUCT DESCRIPTION

Dolphin Fire-Stop Silicone Sealant is an ultimate fire protection solution. It is powerful & flexible single component, neutral cure, gun – grade fire sealant providing optimum unprimed adhesion to different construction substrates. It is an elastomeric, high-performance sealant capable of meeting the joint movement requirements in fire – rated joints and pipe penetrations. Dolphin Fire – Stop is tested for up to 4 hours fire rating at Efectis and UAE Civil Defense approved laboratories and is approved for both penetrations and joint applications in horizontal and vertical fire segments.

TECHNICAL PROPERTIES



Properties	Test Method	Specifications
Chemical Base		1-C Silicone
Cure Mechanism		Moisture
Cure Type		Neutral
Joint Movement Capability	ASTM C 719	± 50 %
As Supplied @ 25°C, 50% RH		
Color		Black, Grey, White
Consistency		Homogeneous paste
Density	ASTM D 1475	1.18 ± 0.02 g/ml
Flow Properties	ASTM C 639	0 (non-sag) mm
Skin Over Time	ASTM C 679	Approx. 6 minutes
Tack Free Time	ASTM C 679	Approx. 10 minutes
Depth Cure, 24 Hrs	Lab Test	~ 2.4 mm
As Cured – 7 Days @ 25°C, 50% RH		
Hardness (Shore A)	ASTM D 2240	30 – 35 Points
Tensile Strength	ASTM D 412	≤ 0.50 N/mm ²
Elongation	ASTM D 412	≤ 500 %
Young's Modulus	ASTM D 412	≤ 0.30 Mpa
Service Temp.		-25 to + 400 °C (Based on the backer segments)
Application Temp.		5 to 45 °C

(Information on this data sheet is subject to change without prior notice and should not be used for writing specifications)

(Curing time (Skin Over Time & Tack Free Time) may vary depending on climatic condition during application)

TYPICAL USES



Construction Joints:

- Cables Building Assemblies
- Concrete and CMU
- Gypsum Wallboard
- Sealing of horizontal and vertical linear joints assemblies and fire rated floors

KEY FEATURES


- Non-Corrosive
- Non-Stain
- UV, Water & Weather resistance upon curing
- Antifungal & Antibacterial
- Heat-Resistance up to 400°C

<ul style="list-style-type: none"> Suitable for dynamic and static construction joints <p>Penetrations:</p> <ul style="list-style-type: none"> Steel, Copper and EMT Fiberglass pipe insulation 	<ul style="list-style-type: none"> High-Flexibility
---	--

Color	Dolphin Fire-Stop Silicone Sealant is available in White, Black, and Grey. RAL* colors are available upon request. *Special color orders may require lead time and minimum order quantities.
Packaging	Dolphin Fire-Stop Silicone Sealant is available in standard caulking cartridges (280 ml), packed sausages (600 ml) and 200 Liter drum
Surface preparation	The substrate areas that will be in contact with sealant must be clean, dry, and free of all loose materials, dust, dirt, rust, oil, and other contaminants. Non - porous substrates should be cleaned with a solvent and a clean, lint - free, cotton cloth. Wipe dry immediately with another such cloth before the solvent evaporates from the surface. Porous surfaces may need to be grinded, free of dust and cleaned
Joint design	<p>For General Use</p> <ul style="list-style-type: none"> • joints up to 12 mm wide, width to depth ratio = 1:1 $\frac{\text{width}}{\text{depth}} = \frac{1}{1} \text{ or } w = d$ • joints over 12 mm wide, width to depth ratio = 2:1 $\frac{\text{width}}{\text{depth}} = \frac{1}{0.5} \text{ or } w = 2d$  <p>MAXIMUM WIDTH FOR SILICONE SEALANT IS 30 MM Install backing material, spacer, or joint filler to ensure correct depth to width ratio is achieved according to design. Apply masking tapes to areas adjacent to joints to ensure neat sealant lines.</p>
Coverage	COVERAGE IN LINEAR METER = $\frac{\text{MATERIAL VOLUME (ML)}}{\text{WIDTH (mm) X DEPTH (mm)}}$
Back up material	The backing material shall be closed cell polyethylene foam backer rod
Penetration design	 <p>Dolphin Fire-Stop Silicone Sealant has been developed for use in small penetration seal applications where it should be used in conjunction with specified backing material</p>



WORLD-CLASS
CHEMICALS

	<ul style="list-style-type: none"> • Dolphin Fire-Stop Silicone Sealant • Dolphin Fire Retardant PU Foam, PE foam, rockwool
Surface preparation	The substrate areas that will be in contact with sealant must be clean, dry, and free of all loose materials, dust, dirt, rust, oil, and other contaminants. Non - porous substrates should be cleaned with a solvent and a clean, lint - free, cotton cloth. Wipe dry immediately with another such cloth before the solvent evaporates from the surface.
Application instruction	Application surface should be dry and dust, rust and grease-free. Cut the nozzle at an angle of 45° and apply sealant on a substrate. Tool immediately to spread the sealant against the surface to give it a smooth finish. For additional information please consult the corresponding product data sheets.
Tooling & finishing	Immediately tool sealant after application and before skin formation. Tooling of sealant should be done in one continuous stroke. Remove masking tape immediately after tooling is completed.
Cleanup and removal	Uncured sealant may be removed from tools, equipment, and non-porous surfaces with solvents. For porous substrates, allow the sealant to cure before removal by peeling or other mechanical means. Cured sealant can only be removed mechanically.
Limitation	Not paintable. Transportation temperature should be 5°C to 40°C.
Storage and shelf life	When stored in original unopened container at or below 77°F (25°C) in dry warehouse conditions, Dolphin Fire-Stop Silicone Sealant has a shelf life of 12 months from manufacturing date. Containers should always be kept sealed when not in use.
Handling precautions	Use in well-ventilated area. Direct contact of uncured sealant may irritate eyes and skin. Over exposure to vapor may irritate eyes, nose, and throat. Do not handle contact lenses with sealant on hands. In case of eye contact, flush eyes with water for 15 minutes. Obtain medical attention. In case of skin contact, remove from skin and flush with water.
Certification	 <p>IFC certification Certificate No: IFCC1076 IFC certification Certificate No: IFCC 1323</p> <p>Efectis</p>

KEEP OUT OF REACH OF CHILDREN • KEEP CONTAINER TIGHTLY CLOSED • FOR INDUSTRIAL & PROFESSIONAL USE

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made. AMI reserves the right to change the properties of its products without notice.

